
New as of:

01.2020



InCoris TZI C

Translucent pre-dyed zirconia ceramic blocks and discs for CEREC and inLab

Processing Instructions: Restoration production for crowns and bridges (not valid for USA/Canada)

English



Table of contents

| | | |
|---|---|----|
| 1 | General | 3 |
| | 1.1 Contact information | 3 |
| 2 | Material | 4 |
| 3 | Chemical composition | 5 |
| 4 | Technical data | 6 |
| 5 | Intended use, indications, contraindications and preparation instructions | 7 |
| | 5.1 Intended use | 7 |
| | 5.2 Indications | 7 |
| | 5.2.1 Blocks | 7 |
| | 5.2.2 Discs | 7 |
| | 5.3 Contraindications | 7 |
| | 5.4 General preparation instructions | 8 |
| | 5.5 Preparation of anterior and posterior tooth crowns | 8 |
| 6 | Creating the restoration | 9 |
| | 6.1 Scanning, designing and milling/grinding | 9 |
| | 6.2 Rework of the grounded/milled restoration | 9 |
| | 6.3 Drying before sintering | 10 |
| | 6.4 Sintering | 11 |
| | 6.5 Additional notes: procedure after sintering | 14 |
| | 6.6 Rework | 14 |
| | 6.7 Painting and coating | 15 |
| 7 | Recommended tools and materials | 16 |
| 8 | Fastening instructions | 17 |
| 9 | Removal of inserted restorations and Trepination | 18 |



USA: Rx only

Customer Service Center

Manufacturer's address



1 General

The inCoris TZI C product bears the CE mark in accordance with the provisions of Council Directive 93/42/EEC of June 14, 1993 concerning medical devices.

inCoris TZI C comprises translucent zirconium oxide dyed in the classical colors (A-D) and is intended for use in manufacturing individually designed fully anatomical restorations, (crowns and bridges) which can be polished or enameled after grounding/milling and sintering.

For the USA only

CAUTION: Federal law (USA) restricts sale of this device to or on the order of a physician, dentist, or licensed practitioner.

1.1 Contact information

In the event of technical queries, please use our online contact form at the following address:

<http://srvcontact.sirona.com>

Sirona Dental Systems GmbH
Fabrikstrasse 31
64625 Bensheim
Germany

Tel.: +49 (0) 6251/16-0

Fax: +49 (0) 6251/16-2591

e-Mail: contact@dentsplysirona.com

www.dentsplysirona.com

2 Material

In the case of inCoris TZI C, blocks and discs comprised of zirconia ceramics are used.

These are initially manufactured in a partially sintered state, then enlarged by the inLab and CEREC CAD/CAM systems; they are individually processed to specification, and finally, densely sintered.

The aesthetic features of inCoris TZI C enable application as fully anatomical crowns and bridges.

The advantages of inCoris TZI C include:

- High strength
- Resistance to corrosion
- Good biological compatibility of the product and
- Translucency
- 10 pre-dyed classical colors (A1-A4; B2; B3; C2; C3; D3)

3 Chemical composition

inCoris TZI C consists of yttria stabilized zirconia.

4 Technical data

The following specifications apply to material that is densely sintered in a CEREC SpeedFire or inFire HTC speed sintering furnace.

| | |
|--|-----------------------------------|
| Density: | $6.08 \pm 0.2 \text{ g cm}^{-3}$ |
| Fracture toughness K_{Ic} | $7.1 \text{ MPa m}^{1/2}$ |
| Thermal expansion coefficient (20 - 500 °C): | $11 \cdot 10^{-6} \text{ K}^{-1}$ |
| Bending strength: | > 900 MPa |
| Grain size | $\leq 0.4 \mu\text{m}$ |
| Chemical solubility | < $25 \mu\text{g/cm}^2$ |

inCoris TZI C are available in three block sizes and three disc heights. A total of ten classical colors are available (A-D). The maxi M blocks and discs are limited in terms of the variety of colors.

Block sizes

inCoris TZI C blocks are available in the following block sizes:

- mono L = 20 x 19 x 15.5 mm (LxWxD)
- medi S = 40 x 19 x 15.5 mm (LxWxD)
- maxi M = 65 x 40 x 22 mm (LxWxD)

Block colors

inCoris TZI C blocks are offered 10 classical colors (A1-A4; B2; B3; C2; C3; D3).

The mono L and medi S block sizes are available in the following colors:

- A1; A2; A3; A3.5; A4; B2; B3; C2; C3; D3

The maxi M block size is available in the following colors:

- A1, A2, A3

Disc sizes

The inCoris TZI C discs all have a diameter of 98.5mm and are available in the following disc heights:

- 13mm
- 16mm
- 22mm

Disc colors

All disc heights are available in the colors:

- A1,
- A2,
- A3,
- A3.5

5 Intended use, indications, contraindications and preparation instructions

5.1 Intended use

Manufacturing of individually designed restorations made from inCoris TZI C blocks and disks by means of the Sirona CAD/CAM-Systems CEREC and inLab.

5.2 Indications

Fully anatomical crowns and bridges in the anterior and posterior tooth region, bridges with a maximum of two pontics.

5.2.1 Blocks

inFire HTC speed Sintering Furnace

Sintering with the classic program: Restorations < 8 units

Sintering with the Speed program: Restorations < 8 units

Sintering with the Super Speed program: No Super Speed sintering.

CEREC SpeedFire Sintering Furnace

The software determines the sintering program according to the present indication.

5.2.2 Discs

inFire HTC speed Sintering Furnace

Sintering with the classic program: Restorations ≤ 6 units and without sinter support.

Sintering with the Speed program: Restorations ≤ 6 units and without sinter support.

Sintering with the Super Speed program: No Super Speed sintering.

5.3 Contraindications

- Insufficient oral hygiene
- Insufficient preparation results
- Insufficient tooth structure
- Insufficient space available

5.4 General preparation instructions


- The preparation must be performed with either a chamfer or a shoulder with rounded internal angle.
- The vertical preparation angle should be at least 3°. All transitions from the axial to the occlusal or incisal areas must be rounded off. Flat or plane surfaces are advantageous.

5.5 Preparation of anterior and posterior tooth crowns

Preparation of anterior teeth

The incisal wall thickness of the ceramics should be at least 1.0 mm, the circular wall thickness at least 0.8-1.0 mm.

The tapering crown edge should be 0.5 mm thick.




Preparation of posterior teeth (premolars and molars)

The ceramic thickness should be at least 1.0 mm at the lowest point of the main fissure.

For the cusp design, a ceramic thickness of at least 1.0 mm should be ensured.

The circular ceramic thickness should be 0.8-1.0 mm.

The tapering crown edge should be 0.5 mm thick.



| Connector surface on ... | Minimum connector surface in mm^2 |
|---|--|
| Posterior tooth bridge restoration with a pontic | 9 |
| Posterior tooth bridge restoration with two pontics | 12 |
| Free-end bridge | 12 |

6 Creating the restoration

6.1 Scanning, designing and milling/grinding

Software 4.3 or higher

If you are using software 4.3 or higher, select Sirona / inCoris TZI C in the material dialog. The inCoris TZI C discs are stored in the material dialog as of inLab SW 15.0 or higher.

Details are documented in the "inLab/CEREC SW User Manual".

6.2 Rework of the grounded/milled restoration

After the grinding/milling process and prior to sintering, a diamond burr milling tool has to be used to separate the restoration.

To prevent milling residues from remaining in the fissures, the restoration can be briefly steamed off or cleaned with water and a soft toothbrush.

In the case of dry-milled restorations we recommend that these are freed from dust using a ceramic brush or compressed air.

Make sure you do not inhale abrasive dusts. Use a vacuum system and wear a mask.

Block remains and the block holder do not need to be disposed of separately. They can be disposed of as normal household waste.

6.3 Drying before sintering

No drying is required for dry-milled restorations (with no water cooling).

The following alternatives are recommended for all other restorations:

- 30 minutes at 80°C (176°F) in the drying cabinet
- 10 minutes at 150°C (302°F) in the drying cabinet
- The CEREC software makes a drying program available for the CEREC SpeedFire furnace for drying restorations.

NOTE

In the case of high humidity

In an environment with a high level of humidity, the restorations can absorb moisture after drying. For this reason, sintering must take place within a maximum of one hour after drying.

NOTE

Risk of damaging the restoration

Drying at temperatures above 150°C (302°F) can damage the restoration.

6.4 Sintering

Restorations made from inCoris TZI C have to be sintered in dry conditions.

The Sirona inFire HTC, inFire HTC speed, or CEREC SpeedFire sintering furnaces offer programs with a pre-drying function.

The sintering process should only be performed in a Sirona sintering furnace.

When sintering in the inFire HTC/HTC speed (inCoris TZI blocks and discs), use the pre-programmed inCoris ZI / TZI / TZI C programs.

When sintering in the CEREC SpeedFire (inCoris TZI blocks), the CEREC software automatically selects the program. Observe the information in the operating instructions for the furnace.

As an alternative, the sintering process can be carried out in the compatible VITA Zyrcomat or Ivoclar Vivadent Sintrammat high temperature furnaces. In any case, the details in the manuals for the respective furnaces are to be adhered to.

The classic program for sintering inCoris TZI C is the same as for inCoris TZI and inCoris ZI. The sintering result from furnaces other than those specified here cannot be guaranteed by Dentsply Sirona.

| Heating rate °C/min | Holding temperature °C | Holding time min |
|------------------------|---------------------------|---------------------|
| 25 | 800 | 0 |
| 15 | 1510 | 120 |
| 30 | 200 | 0 |

Since speed sintering is only permitted in inFire HTC speed furnaces with inCoris ZI and inCoris TZI materials, and these programs are permanently installed in the furnace, the programs are not described here. Classic and speed sintering are carried out in the sintering tray provided with the inFire HTC speed furnace.

Sintering in CEREC SpeedFire

When sintering in the CEREC SpeedFire furnace, place the restorations with the occlusal surface directly on the top door insulation.

NOTE


Maximum Observe restoration size

Observe the maximum Furnace chamber size when loading the furnace.

- Diameter: 38 mm
- Height: 20 mm

Sintering in inFire HTC or inFire HTC speed

We recommend following the instructions below precisely because, especially with sintering of occlusally very curved restorations, the correct bead layer is a decisive factor in subsequent fitting on the model:



Restoration on sintering bead layer

- Only use the sintering trays and beads intended for the respective high-temperature furnace when sintering InCoris TZI C.
- Make sure that the restorations are lying completely on the bed of beads.
- Remove beads lying interdentally with a probe, so that shrinking is unhindered.
- If several restorations are sintered at the same time, these must not touch the edge of the sintering tray or each other.



"Embedded" bridge restoration:

- In order to prevent the sintering beads from sticking (e.g. interdental on the bridge pontic), the restorations must not be pressed or "embedded" into the sintering beads too hard.



Very occlusally curved bridge restorations lying on buccal restoration side:

- Position crown and bridge restorations on the **occlusal** side of the restoration.
- Very occlusally curved bridge restorations (e.g. Spee's curve) are always to be placed on the **buccal / labial** side of the restoration so that the center bend of the restoration is lying on the sintering beads.
- Use additional sintering beads to support ends of restorations which have hollow areas.



Non-supported bridge restoration (with hollow area)

- Support every restoration pontic with at least one sintering bead so that bridge restorations are adequately supported along the entire length of the restoration and do not "lie hollow".

Notes on sintering in an inFire HTC speed from serial numbers 5000 to 5699

NOTE

Reprogramming heat curves

As a result of a modified component in inFire HTC speed from serial numbers 5000 to 5699, depending on the local power grid your furnace may show signs of an increased heating rate. Please program the following heat curves for inCoris TZI C and use this or the "classic" program for sintering.

For speed sintering "speed":

On a program station from 20 to 26:

| | Heating speed °C/min | Holding temperature °C | Holding time min |
|----|-------------------------|---------------------------|---------------------|
| S4 | 99 | 750 | 0 |
| S3 | 99 | 1100 | 0 |
| S2 | 50 | 1510 | 30 |
| S1 | 99 | 800 | 5 |

For speed sintering with pre-drying "speed + dry":

On program station 27 or 28:

| | Heating speed °C/min | Holding temperature °C | Holding time min |
|----|-------------------------|---------------------------|---------------------|
| S4 | 99 | 750 | 0 |
| S3 | 50 | 1510 | 30 |
| S2 | 99 | 800 | 5 |
| S1 | 15 | 80 | 30 |

For speed sintering "speed + air":

On program station 29 or 30:

| | Heating speed °C/min | Holding temperature °C | Holding time min |
|----|-------------------------|---------------------------|---------------------|
| S4 | 99 | 750 | 0 |
| S3 | 99 | 1100 | 0 |
| S2 | 50 | 1510 | 30 |
| S1 | 99 | 500 | 0 |

6.5 Additional notes: procedure after sintering

In the case of yellow staining of restorations after the sintering process, the high-temperature furnace should be cleansed by performing an empty run. The details in the manuals for the respective furnaces are to be adhered to in this case.

This is not necessary with CEREC SpeedFire due to the different heating concept.

Sintering beads that adhere are to be removed carefully.

After the sintering process, the restorations must be cooled down to room temperature before further processing.

6.6 Rework

The surface condition of ceramic materials is decisive for their bending strength. Reworking sintered restorations with milling tools, especially in the connector region, must be avoided at all costs.

Therefore make corrections to the milled/ground restoration if possible before sintering.

However, if reworking should be necessary, comply with the following basic rules:

- Reworking in the sintered condition should be performed with a wet grinding highspeed handpiece (approx. 2.5 – 3 bar) or rubber polishers (low speed) or for primary telescopes with a milling unit using water cooling and with low grinding pressure. As an alternative it is possible to rework with soft, diamond rubber polishers and a handpiece at low speed and low pressure. The tool must be applied flat and must not “clatter”.
- New diamond grinders with varied grain size should be used if possible.
- Areas that are under tension in clinical use, i.e. primarily the connectors in bridge structures, should not be ground.

The sintered restorations should also be polished prior to applying the enamel coating in order to prevent abrasion to the antagonist following potential loss of shine.

The inCoris TZI C can be polished with all standard polishing agents for zirconia ceramics. Subsequent heat treatment (depressurization fire) is not necessary.

6.7 Painting and coating

Restorations from inCoris TZI C can be finalized using all standard paint and gloss colors for zirconia ceramics, e.g. VM9 from Vita. In this case the manufacturer's processing instructions must be observed without fail.

Using the CEREC SpeedGlaze spray is recommended for glazing. It is ideally suited to inCoris TZI C.

7 Recommended tools and materials

- Modeling wax
 - Scan wax (Sirona) (suitable for scans with the inLab scanner, not for exposures with inEos)
- Wet grinding turbines:
 - KaVo K-AIR plus (KaVo);
 - IMAGO (Steco-System-Technik GmbH & Co.KG);
 - NSK Presto Aqua (Girrbach);
 - Turbo-Jet (Acurata)
- Grinding tools for reworking with the wet grinding turbine/with handpiece
 - Diamond grinding element sets Ceramic-Line, Telescope-Line (Sirius Dental Innovations).
 - Diamond porcelain polisher for handpiece, green-orange (Hager & Meisinger, Art. No. HP 803 104 372 533 170).
 - Diamond polisher for handpiece (green and orange), EVE Diacera.
- Other:
 - Suitable colored contact materials
- Preparation sets:
 - Preparation set acc. to Küpper (Hager & Meisinger, Art. No. 2560);
 - Preparation set acc. to Baltzer and Kaufmann (Hager & Meisinger, Art. No. 2531);

8 Fastening instructions

Restorations made from inCoris TZI C can be fastened non-adhesively with glasionomer or zinc phosphate cements, or adhesively with the self-curing PANA VIA™ 21 TC composite (Kuraray), the dual-curing PANA VIA™ F composite (Kuraray), or the Calibra® UNIVERSAL cement (Dentsply).

Pre-treatment of the restoration before adhesive bonding:

- Sand-blast the internal surfaces of the restoration in the one-way blasting process with max. 50 µm corundum (Al₂O₃). Pressure < 2.5 bar.
- Do not touch the sandblasted surface if at all possible.

9 Removal of inserted restorations and Trepination

Removal of inserted restorations

In order to remove a fixed zirconium restoration, we recommend using a cylinder-shaped diamond tool with the maximum amount of water cooling and a speed of 120,000 rpm to separate the restoration.

Trepination

The restoration can be trephined with a coarse-grained, spherical diamond with ample irrigation and a speed of 120,000 rpm.

In this case, it is recommended that the instrument is applied in a circular motion at an angle of 45° when drilling through the framework.

We reserve the right to make any alterations which may be required due to technical improvements.

© Sirona Dental Systems GmbH
D3487.201.09.07.02 01.2020

Sprache: englisch
Ä.-Nr.: 128 779

Printed in Germany

Sirona Dental Systems GmbH



Fabrikstr. 31
64625 Bensheim
Germany
www.dentsplysirona.com

Order No **64 93 550 D3487**